

CHARACTERISTICS	SPECIFICATIONS	ANALYSIS METHOD
SiO ₂ (Anhydrous), %	98 Min.	MI-05-033
Moisture Loss at 105°C, %	3.0 - 6.0	MI-05-022
Loss on Ignition (at 1050°C), %	4.0 - 6.0	MI-05-022
pH (5% water suspension)	6.0 - 7.5	MI-05-025
Soluble Salts Content, %	3.5 Max.	MI-05-030
DBP Absorption, ml/100g	280 - 290	MI-05-029
Tapped Density, g/l	130 Min.	MI-05-027
BET Surface Area, m ² /g	170 - 200	MI-05-031
Sieve Residue >45µin, %	5.0 Max.	MI-05-028
Arsenic, mg/kg	0.5 Max.	MI-05-120
Cadmium, mg/kg	0.5 Max.	AAS
Copper, mg/kg	2.0 Max.	AAS
Mercury, mg/kg	0.1 Max.	AAS
Lead, mg/kg	2.0 Max.	MI-05-121

Documento Versión Web / Estimado Cliente: Antes de realizar su compra solicite la última versión de este documento.